RG104 E-1 Box 121

1880

Weekly Report of Gold Deposits Melted at United States Mint.

Date.	Assay No.	Name of Depositor.	Weight before Melting. oz.	dec.	Weight after Melting. oz.	dec.	Loss. oz.	dec.	Loss per ct.		Gain. oz.	dec.	Description of Bullion.	Notes of Melter & Refiner.
May 24th	830	Wm. B. Lee	57	74	57	70		04		07			Bar	The deposits are from the
	1	Eugene McClellan	10	87	9	34	1	33	12	12			Jewelry & Melt Cases	following sources:
	2	G. C. Thompson	15	50	12	88	2	62	17	49			Melt Cases & Jewelry	Virginia (1) 2
	3	Do	52	57	34	11	28	46	53	70			Scrap in Wagonia boxes	N. Carolina (1) 3
	4	Do	11	69	10	88		81	6	75			Jewelry	Georgia (1) 1
	5	M. McMichael, Jr, Cash'r	60	90	60	86		04		07			U.S. & For. Coin	Tennessee 1
	6	Hastings & Co.	38	18	37	46		72	1	89			Bullion, Bars & Leaf	Colorado (1) 1
25th	7	Ziegler Bros.	3	78	3	60		18	4	50			Ors, Va.	Finer Bullion (3) 7
	8	A. London Snowden, Supt.	90	26	90	25		01		01			Bars & Prices, N.C. Mint	Bazer " " (1) 3
26th	9	G. C. Thompson	5	38	5	37		01		20			Bar, Col.	Jewelry. 7
	40	Do	6	80	6	80							Bullions	very base bullion 3
	1	Do	37	15	23	69	3	46	12	81			Bullion, Base	Dental plate 2
	2	Do	17	95	16	98		97	5	39			Bullion	Coin, &c 4
	3	Do	15	57	14	05	1	52	9	50			Bars, Skilips & Sweeps	Total 34
	4	Do	7	80	7	49		31	3	87			Amt, N. C.	The losses in melting
	5	Drexel & Co.	49	69	49	68		01		02			For. & U.S. Coin	the Grains from Virginia
	6	Do	9	25	8	76		49	5	44			Amt, Wyoming	4½%; the amalgam
	7	Phillips & Sachs	64	48	64	48							U.S. Coin	from N. Carolina,
	8	J. C. White	17	13	16	84		39	1	71			D'Pt & Fillings	3.87%, and from Wyo-
27th	9	John Smith Receipt 628.33	778	75	625	18	153	57	19	71			Crushed Quartz & Bar	ming 5.54%; the
	50	G. C. Thompson	29	37	29	00		37	1	28			Bars, Va, Base	mint metal from N. Ca-
	1	Do	7	54	7	53		01		12			Bar, Gen.	rolina, 4.40%, and
	2	Do	18	30	17	26	1	04	5	78			Amt Ors, Tenn.	from Tennessee 5.78%;
	3	H. N. Ebey	8	07	8	07							Bullion	— are all & each severally
	4	G. C. Thompson	19	62	17	73	1	89	9	45			Melt Cases & Jewelry	within reasonable lim-
	5	A. Humbert	41	72	41	69		03		07			Bar	its; the losses on finer
	6	H. H. Lyon	12	87	12	85		02		15			U.S. & For. Coin & Jewelry	bullion, 0.16%, on
	7	G. C. Thompson	8	88	8	12		76	8	44			Jewelry	baser bullion 4.07%,
28th	8	Do	22	25	21	19	1	06	4	82			Melt Cases, Jewelry & Silver	jewelry & the like, 8.47%
	9	Do	11	96	11	92		04		33			Ring	and on very base bullion
	60	Do	5	08	4	86		22	4	40			Amt Ors, N. C.	28.74%, are all & each
	1	Do	10	67	10	26		41	3	73			Jewelry & Melt Cases	legitimate, that on
	2	Simons, Bro. & Co.	97	56	97	23		33		34			Bars	jewelry being the least
	3	G. C. Thompson	35	64	35	47		17		47			Ring Silver	tests general ratio.
	4	Do	11	22	10	99		23	2	09			Bar, Melt Cases & Jewelry	Jas. B. Booth
			168	89	148	47	20	42	12	56				Melt. R.

For week ending May 29th 1880

Approximate value, $ 22,947.28

To the Director of the Mint.

S. Bobby Baughman

Register.

RG104 E-1 Box 121

Report of Gold Deposits melted for week ending :—

May 25th 1880

NARA RG104, Entry 1, Box 121

[Abstract:] Report of Gold Deposits melted for weeks ending: -

May 28, 1880

Weekly Report of Gold Deposits Melted at United States Mint.

[Please see original images for data table.]